



## HTV Application & Wash Guidelines

Issue Date: 07/10/20

	Item	Temperature (°C)	Pressing time (Sec.)	Type of Peel	Washing (Up to)
Cad-Cut	One Flex	150°C	5	Hot / Warm / Cool	60°C
		140°C	8		
		130°C	10		
		120°C	15		
	Premium Glitter	160-170°C	15	Hot / Cool	60°C
	Metallic & Holographic	150°C	10-15	Hot / Cool	60°C
	Brushed PU	180°C	10	Warm	60°C
	Stretch Metallic	140°C	7 (Direct 3)	Warm / Cool	Wool Cycle-40°C
	Flock	150°C	10	Cool	60°C
	Ultra Reflective	150°C	10	Warm / Cool	60°C
	Luminous	150°C	10	Warm / Cool	40°C
	Ultra Soft Metallic	150°C	10	Cool	60°C
	PU Block Out White	150°C	10	Warm	60°C
	Silicone Ultra 200 & 500	150°C	10	Cool	60°C
	Chameleon Flex	150°C	10-15	Warm	40°C
	Shimmer Flex	150°C	5	Cool	40°C
	Design Film	150°C	10	Warm	40°C
	UV Sensitive	150°C	10	Warm	40°C
	Carbon PU	150-150°C	8-10	Warm	40°C
	Puff PU	165-175°C	8-10	Warm	40°C
Subli Flock	160 + 190-200°C	4 + 20-25	Cool	40°C	
Subli Fabric	160 + 190-200°C	4 + 20-25	Cool	40°C	
Printable	White	150°C	10	Hot / Warm / Cool	60°C
	Transparent / Silver / Luminous	150°C	10	Warm	40°C
	Glitter	160°C	10-15	Warm	60°C
	Subli Block PU	150°C	10	Warm	60°C